



Faculty of Engineering

The Temperature Effects of Titanium Dioxide (TiO_2) Doped Reduced Graphene Oxide (rGO) for Perovskite Solar Cell Application

Rafidah Binti Kemat

**Master of Engineering
2020**

The Temperature Effects of Titanium Dioxide (TiO₂) Doped Reduced Graphene Oxide (rGO) for Perovskite Solar Cell Application

Rafidah Binti Kemat

A thesis submitted

In fulfilment of requirements for the degree of Master of Engineering

(Electronic Engineering)

Faculty of Engineering
UNIVERSITI MALAYSIA SARAWAK
2020

DECLARATION

I declare that the work in this thesis was carried out in accordance with the regulations of Universiti Malaysia Sarawak. It is original and is the result of my work, unless otherwise indicated or acknowledged as referenced work. This thesis has not accepted for any degree and is not concurrently submitted in candidature for any other degree.

Name of Student : Rafidah Binti Kemat
Student ID No : 17020130
Programme Degree : Master Degree (Electronic Engineering)
Faculty : Faculty of Engineering
Thesis Title : The Temperature Effects of Titanium Dioxide (TiO₂) Doped
Reduced Graphene Oxide (rGO) for Perovskite Solar Cell
Application

Signature of Student :

Date :

ACKNOWLEDGEMENT

Alhamdulillah, all praises to Allah the Almighty, to whom we belong and without His graces and blessings, I would not have made this journey possible. I would like to take this opportunity to thank the following people who have given me invaluable, unlimited and cheerful helps during my research. My first appreciation dedicated to my supervisor, Dr Siti Kudnie Sahari and co-supervisor, Dr Muhammad Kashif for all the guidance, knowledge and for constructive feedbacks they gave me throughout this journey. I am very thankful as I am the receiver of ZAMALAH UNIMAS scholarship throughout my study. I also would like to acknowledge the grant from Ministry of Higher Education Malaysia, the Fundamental Research Grant Scheme (FRGS) in funding and supporting my research. I would like to thank Afiqah Baharin, my research member academically and my best buddy socially, for countless help and supports, for the knowledge you shared with me and for the positive vibes you gave me. Thank you for always be there for me and I would not have done it without her. Mount of special thanks to the technicians in Faculty of Engineering, UNIMAS especially to Mr Sabariman Bakar and Mr Airul Azhar for their valuable time and assistance during this study. Last but not least, a grateful appreciation would like to be dedicated to my dearest family, especially to my parents, Mr Kemat Bin Sais and Mdm Rohani Binti Bakar for their endless supports and for kept believing in me. Not to forget, my beloved friends for their thought, prayers and supportive words they gave me. I am beyond grateful for their presence in my life and I am sincerely wish them the best in everything they do.

ABSTRACT

Perovskite solar cells (PSC) are evolving in spectacular pace and emerging as the most promising future generation of photovoltaic devices. In the present study, reduced graphene oxide (rGO) is introduced to titanium dioxide (TiO₂) as electron transport layer (ETL) in perovskite solar cell (PSC). TiO₂ doped rGO (TiO₂/rGO) was prepared by combining titanium (IV) oxide nanopowder as precursor for TiO₂ and chemically reduced graphene oxide for rGO. The TiO₂/rGO is varied with different annealing temperature and its effect on TiO₂/rGO properties and on electrical performance of PSC is studied. The surface morphologies of TiO₂/rGO thin films is characterized via Scanning Electron Microscope (SEM), Atomic Force Microscope (AFM) and X-Ray Diffraction (XRD). Meanwhile, Ultraviolet-visible spectroscopy (UV-Vis) and X-ray Photoelectron Spectroscopy (XPS) are used to characterize the optical properties and chemical bonding respectively. Lastly, (I-V) analysis for electrical properties is performed. Structural and morphological evidences from SEM, AFM and XRD results confirmed that the TiO₂/rGO samples existed in anatase phase, rutile phase and the porosity as well as the surface roughness of TiO₂/rGO thin films increased as the annealing temperature increased. The absorption spectra and the band gap obtained at 326 nm and 2.48 eV respectively for TiO₂/rGO that annealed at 550 °C portraits better performances due to increment in grain size in higher annealing temperature. The formations of Ti-O and Ti-O-C bonds are confirmed from XPS analysis that fastening the rate of electron transfer in PSC. The electrical properties of TiO₂/rGO confirming that 550 °C TiO₂/rGO has better conductivity at 18.83×10^{-3} S/cm in conjunctions with its performance in optical properties.

Keywords: Doping, perovskite solar cell, reduced graphene oxide, titanium dioxide.

***Kesan Suhu Doping Titanium Dioksida (TiO₂) dengan Grafin Kurang Oksida (rGO)
untuk Aplikasi Sel Solar Perovskite***

ABSTRAK

Sel solar perovskite (PSC) telah berkembang dengan pesat dan muncul sebagai prospektif generasi masa depan untuk peranti fotovoltaiik. Dalam kajian ini, grafin kurang oksida (rGO) dicampurkan dengan titanium dioksida (TiO₂) sebagai lapisan electron penghantar (ETL) dalam sel solar perovskite (PSC). Doping TiO₂ dengan rGO (TiO₂/rGO) telah dihasilkan melalui penggabungan titanium oksida (IV) dalam serbuk nano sebagai pendahulu untuk TiO₂ manakala rGO melalui pengurangan kimia daripada grafin oksida. TiO₂/rGO dihasilkan dengan suhu penyepuhlindapan yang berbeza dan kesannya terhadap sifat TiO₂/rGO dan prestasi elektrik dalam PSC dicatatkan. Mofologi permukaan filem tipis TiO₂/rGO dianalisa melalui Pengimbasan Elektron Mikroskop (SEM), Mikroskop Angkatan Atom (AFM) dan Difraksi X-Ray (XRD). Sementara itu, Spektroskopi Ultraviolet (UV-Vis) dan X-ray Photoelectron Spektroskopi (XPS) digunakan untuk mendapatkan sifat optik dan ikatan kimia. Akhirnya, analisis (I-V) untuk prestasi elektrik dilakukan. Struktur dan morfologi yang diperolehi daripada keputusan SEM, AFM dan XRD mengesahkan bahawa sampel TiO₂/rGO wujud dalam fasa anatase, fasa rutil dan keliangan serta kekasaran permukaan filem nipis TiO₂/rGO meningkat apabila suhu penyepuhlindapan meningkat. Spektrum penyerapan dan jurang band yang diperolehi pada 326 nm dan 2.48 eV menunjukkan bahawa TiO₂/rGO yang anil di 550 °C mempamerkan prestasi yang lebih baik disebabkan kenaikan dalam saiz butiran dalam suhu penyepuhlindapan yang lebih tinggi. Pembentukan ikatan Ti-O dan Ti-O-C disahkan dari analisis XPS mengawal kadar pemindahan elektron dalam PSC. Prestasi TiO₂/rGO dari segi elektrik mengesahkan

bahawa 550 °C TiO₂/rGO mempunyai kekonduksian yang lebih baik pada $18.83 \times 10^{-3} \text{ S/cm}$ bertepatan dengan prestasinya dalam sifat optikal.

Kata kunci: *Doping, sel solar perovskite, grafin kurang oksida, titanium dioksida.*

TABLE OF CONTENTS

	Page
DECLARATION	i
ACKNOWLEDGEMENT	ii
ABSTRACT	iii
<i>ABSTRAK</i>	iv
TABLE OF CONTENTS	vi
LIST OF TABLES	xi
LIST OF FIGURES	xii
LIST OF ABBREVIATIONS AND SYMBOLS	xiv
CHAPTER 1: INTRODUCTION	1
1.1 Research Overview	1
1.2 Research Problem Statement	4
1.3 Research Hypothesis	5
1.4 Research Gap	6
1.5 Research Objectives	7
1.6 Scope of Research	7
1.7 Structure of Thesis	8
CHAPTER 2: LITERATURE REVIEW	10
2.1 Introduction	10

2.2	Titanium Dioxide (TiO ₂)	10
2.2.1	Introduction of TiO ₂	10
2.2.2	Structure of TiO ₂	11
2.2.3	Synthesis Methods of TiO ₂	14
2.2.3.1	Sol-gel Technique	14
2.2.3.2	Precipitation Method	16
2.2.3.3	Microemulsion Technique	17
2.2.3.4	Hydrothermal Method	18
2.2.3.5	Salvothermal Method	19
2.2.3.6	Summary of Synthesis Method for TiO ₂	20
2.2.4	Addition of Polymer in TiO ₂	21
2.3	Reduced Graphene Oxide (rGO)	22
2.3.1	Introduction of rGO	22
2.3.2	Synthesis Methods of GO	23
2.3.2.1	Summary for Synthesis Method of GO	25
2.3.3	Synthesis Method of rGO	26
2.3.3.1	Chemical Reduction	27
2.3.3.2	Thermal Reduction	28
2.3.3.3	Multi-Step Reduction	29
2.3.3.4	Summary for Synthesis Method of rGO	30
2.4	Titanium Dioxide (TiO ₂) Doped Reduced Graphene Oxide (rGO)	31

2.5	Perovskite Solar Cell	33
2.5.1	Perovskite Solar Cell Overview	33
2.5.2	Perovskite Solar Cell Structure	36
2.5.3	Perovskite Solar Cell Configuration	37
2.5.3.1	Mesoporous Configuration	37
2.5.3.2	Planar Configuration	39
2.5.4	Perovskite Working Principles	40
2.5.5	Perovskite Charge Transport Buffer Layers	42
2.5.5.1	Hole Transport Material (HTM)	42
2.5.5.2	Electron Transport Material (ETM)	43
2.6	Summary	45
CHAPTER 3: METHODOLOGY		46
3.1	Introduction	46
3.2	Designation of Perovskite Solar Cell	46
3.2.1	Glass Substrate Layer	47
3.2.2	Compact TiO ₂ Layer	48
3.2.3	Electron Transport Layer (ETL)	49
3.2.3.1	Preparation of Graphene Oxide (GO) solution	50
3.2.3.2	Preparation of Reduced Graphene Oxide (rGO) Solution	53
3.2.3.3	Preparation of Titanium dioxide (TiO ₂) Solution	54
3.2.3.4	Preparation of TiO ₂ doped rGO Solution and Layer Deposition	56

3.2.4	Perovskite Layer	57
3.2.5	Hole Transport Layer (HTL)	58
3.2.6	Metal Electrode	59
3.2.7	Summary of Perovskite Solar Cell Fabrication	60
3.3	Characterization of TiO ₂ doped rGO (TiO ₂ /rGO) and Perovskite Solar Cell	61
3.3.1	Surface Morphological Characterization	61
3.3.2	Optical Characterization	63
3.3.3	Chemical Bonding Analysis	64
3.3.4	Electrical Characterization	65
CHAPTER 4: RESULT AND DISCUSSION		67
4.1	Overview	67
4.2	Surface Morphology	67
4.2.1	Scanning Electron Microscopy (SEM)	67
4.2.2	Atomic Force Microscopy (AFM)	70
4.2.3	X-ray Powder Diffraction (XRD)	72
4.3	Optical Characterization	75
4.3.1	Ultraviolet-visible Spectroscopy (UV-Vis)	75
4.4	Chemical Bonding Analysis	78
4.4.1	X-ray Photoelectron Spectroscopy (XPS)	78
4.4.1.1	Ti2p XPS Data of TiO ₂ /rGO	78
4.4.1.2	C1s XPS Data of TiO ₂ /rGO	80

4.4.1.3	O1s XPS Data of TiO ₂ /rGO	82
4.5	Electrical Properties of TiO ₂ /rGO PSC	84
CHAPTER 5: CONCLUSION AND RECOMMENDATION		88
5.1	Overview	88
5.2	Conclusion of Research Finding	88
5.3	Recommendation	90
REFERENCES		91

LIST OF TABLES

	Page
Table 2.1 Summary of TiO ₂ with different phase	13
Table 2.2 Synthesis method of TiO ₂ with resultant phases	20
Table 2.3 Summary for synthesis method of GO	25
Table 2.4 Summary for synthesis method of rGO	30
Table 3.1 Descriptions of each furnace setting	56
Table 4.1 Analysis of XRD patterns	74
Table 4.2 Energy band gap of TiO ₂ /rGO at different annealing temperature	78
Table 4.3 Electrical properties of TiO ₂ /rGO PSC at different annealing temperature	86

LIST OF FIGURES

	Page
Figure 1.1 PCE for conventional photovoltaics	2
Figure 2.1 Crystal structure of TiO ₂ phases	12
Figure 2.2 Porous structure of GO/TiO ₂ before and after heat treatment	32
Figure 2.3 Generation of photovoltaics	34
Figure 2.4 Perovskite ABX ₃ structure with BX ₆ octahedral	36
Figure 2.5 Schematic of mesoporous structure	38
Figure 2.6 Schematic of planar structure	39
Figure 2.7 Charge transport channel in PSC	41
Figure 3.1 Cross sectional layer of perovskite solar cell	47
Figure 3.2 Vacuum spin coater	48
Figure 3.3 Process flow for the preparation of mesoporous TiO ₂ /rGO layer	49
Figure 3.4 The Preparation Step of GO Solution	52
Figure 3.5 (a) Reflux method, (b) rGO solution	53
Figure 3.6 Flow Chart for Preparation of rGO Solution	54
Figure 3.7 450 °C annealing temperature graph	55

Figure 3.8	450 °C, 550 °C and 650 °C TiO ₂ /rGO samples	57
Figure 3.9	(a) Homemade mask, (b) Perovskite solar cell after Au coating	59
Figure 3.10	Schematic Illustration for Perovskite Solar Cell Fabrication	60
Figure 3.11	Keithley Sourcemeter	65
Figure 4.1	SEM images at 1k magnification	68
Figure 4.2	SEM images of TiO ₂ /rGO at different annealing temperatures	69
Figure 4.3	AFM images of of TiO ₂ /rGO at different annealing temperatures	71
Figure 4.4	XRD patterns of TiO ₂ /rGO at different annealing temperatures	73
Figure 4.5	UV-Vis spectra of TiO ₂ /rGO at different annealing temperatures	76
Figure 4.6	Tauc Plot of TiO ₂ /rGO at different annealing temperature	77
Figure 4.7	XPS spectra of Ti2p	80
Figure 4.8	XPS spectra of C1s	82
Figure 4.9	XPS spectra of O1s	83
Figure 4.10	I-V characteristic TiO ₂ /rGO PSC at different annealing temperature	85

LIST OF ABBREVIATIONS AND SYMBOLS

Al_2O_3	Aluminium oxide
Au	Gold
C	Carbon
C-C	Carbon-carbon
C-O	Carbon-oxygen
COOH	Carboxylic
$\text{CH}_3\text{NH}_3\text{PbBr}_3$	Methylammonium lead bromide
$\text{CH}_3\text{NH}_3\text{PbI}_3$	Methylammonium lead iodide
DMF	Dimethylformamide
ETL	Electron transport layer
ETM	Electron transport material
FTO	Fluorine doped tin oxide
GO	Graphene oxide
HTL	Hole transport layer
HTM	Hole transport material
H_2O	Water
H_2O_2	Hydrogen peroxide
H_2SO_4	Sulfuric acid
H_3PO_4	Phosphoric acid
KMnO_4	Potassium permanganate
Li-TFSI	Lithium bis(trifluoromethanesulfonyl)imide
O	Oxygen

OH	Hydrogen
PbI ₂	Lead (II) iodide
PEG	Polyethylene glycol
PSC	Perovskite solar sell
rGO	Reduced graphene oxide
Spiro-OMeTAD	2',7,7'-tetrakis-(N,N-di-p-methoxyphenylamine)-9,9-spirobifluorene
TCO	Transparent conducting oxide
Ti	Titania
TiO ₂	Titanium dioxide
TiO ₂ /rGO	Titanium dioxide doped reduced graphene oxide
TTIP	Titanium isopropoxide
ZnO	Zinc oxide
σ	Resistivity
ρ	Conductivity

CHAPTER 1

INTRODUCTION

1.1 Research Overview

Renewable energy tender opportunity of carbon-free economy for a greener and sustainable energy development in the world whereas the non-renewable energy sources produced enormous amount of carbon dioxide (CO_2) that harmful to environment and contribute to the hikes in climate changes and global warming (Nematollahi et al., 2016). Solar energy harvesting has been done substantially through photovoltaic devices as energy supply from the sun is reliable, renewable, and sustainable with no worry of depletion (Papoola et al., 2018). Thin film based photovoltaics solar cell such as copper-indium-gallium-selenide (CIGS), cadmium telluride (CdTe), dye-sensitized solar cell (DSSC), organic solar cell and perovskite solar cell (PSC) especially have caught research attention whereas by 2030 photovoltaic are anticipated as the third of global electricity generation (Green et al., 2014).

Perovskite solar cell has shown an increase in power conversion efficiency (PCE) at phenomenal rate in just seven years as compared to other type of photovoltaics. Perovskite is an organic-inorganic material that have shown its own capabilities for the use in light-emitting diodes, sensors, field-effect transistors and photodetectors (Assadi et al., 2018). Perovskite solar cells belong to the family of third generation of solar cell. The third generation of solar cell uses organic material in its fabrication that cut down the cost of making a solar cell. Perovskite solar cell also has display special combination of ambipolar charge transport properties, good broadband absorption and long carrier diffusion (Tonui et al., 2018).




Figure 1.1: PCE for conventional photovoltaics (Best Research-Cell Efficiency Chart. (n.d.).

The first published perovskite solar cell was fabricated with methylammonium lead bromide ($\text{CH}_3\text{NH}_3\text{PbBr}_3$) as perovskite sensitizer and recorded 3.5% of power conversion efficiency (PCE) in 2009 (Tonui et al., 2018). Interestingly, the efficiency jumped to >15% after seven years later by making the perovskite material solid and cell design simpler with the use of methylammonium lead iodide ($\text{CH}_3\text{NH}_3\text{PbI}_3$) as perovskite material (Wu et al., 2014; Asghar et al., 2017). The high efficiency enabled the perovskite to compete with another conventional established technologies as shown in Figure 1.1. This dramatic increase in efficiency is due to the perovskite-based absorbers itself where it has larger capability to absorb photons than other conventional materials in making solar cells. In fact, it beats the industry-leading material silicon which it can absorb a larger spectrum of light (Mehmood et al., 2017).

Relatively, perovskite solar cells have two different configurations which are the meso-superstructured PSC and planar heterojunction PSC (Allesandro et al., 2016). In meso-superstructured device, the mesoporous layer typically made of metal oxide such as nano-crystalline titanium dioxide (TiO_2) and aluminium oxide (Al_2O_3) as scaffold infiltrated with perovskite solar cell. In this research, the nanocomposites reduced graphene oxide (rGO) and titanium dioxide (TiO_2) nanoparticles were utilized as electron transport layers in meso-superstructured perovskite solar cell. It has been reported that graphene- TiO_2 nanocomposites has the benefits of high conductivity and better electrical contacts of graphene and graphene-like materials for electron transporting. Furthermore, the highest PCE reported graphene-PSC works so far was done by Nicholas which had shown remarkable PCE up to 15.6% (Nicholas, 2013). This shows that the integration of graphene into PSC can compete with other intrinsic PSC in term of power conversion efficiency.

Further study on the graphene-PSC integration by using reduced graphene oxide (rGO) that synthesized through improved Hummer's method and chemical reduction is conducted in this research. The hole transporting layers (HTM) used in the PSC is highly expensive due to synthesis complexity. The material of choices here is 2,2',7,7'-tetrakis-(N, N-di-p-methoxyphenylamine)-9,9'-spirobifluorene (spiro-oMETAD) which has been well studied due to its popularity in solid state dye solar cells (DSCs). In addition, its tendency to be uncontrollably doped by O^2 which necessitate the development of alternatives. An application of nanocarbons such as graphite, carbon nanotubes, and graphene/polymer composites based hole transporters is one of alternative worth to further investigated.

Next, the synthesis, characterization and the application of titanium dioxide doped reduced graphene oxide (TiO_2/rGO) as mesoporous layer in the fabrication of perovskite solar cell were studied and discussed. The performance TiO_2/rGO thin film and TiO_2/rGO -

based perovskite is varied by the annealing temperature of titanium dioxide to enhance the electrical performances of perovskite solar cell.

1.2 Research Problem Statement

Resources for a clean and renewable energy is one of the challenges that our society have to face in order to allay with the rapidly increasing demand for the developing population and industrialization. The usage of non-renewable energy such as fossil fuels and others have contributed to rise of atmospheric temperature and high level emission of carbon dioxide (CO_2) that associated with the greenhouse effect (Khalaji et al., 2018). A lot of studies have been executed for solar energy harvesting that has been performed through photovoltaic devices. PSCs have been dominating research interest due to its impressive development in power conversion efficiency (PCE) that have reached 20% in over seven years of research as compared to other type of solar cell (Tonui et al., 2018). In spite of that, further improvement are imperative to optimize and enhance the PSC devices operation, stability and device performance. The aim is to construct photovoltaic device, an argonometal halide perovskite solar cell with $\text{CH}_3\text{NH}_3\text{PbI}_3$ as the absorber that coated upon the surface of mesoporous TiO_2/rGO .

Throughout the years, anatase TiO_2 was found to be the most common material to enhance photocatalytic properties of photoanodes in solar cell due to its long-term thermodynamic stability, low cost and relatively non-toxicity (Kang et al., 2019). However, the drawbacks are anatase TiO_2 tend to suffer from high recombination center of electrons and hole coupled with wide band gap which is 3.2 eV (Tan et al., 2013).

On the other hand, graphene has been widely used in application of optoelectronic and photon energy conversion due to its unique mechanical and electrical properties (Lundie et al., 2015; Chong et al., 2016). Some research was conducted and it is reported that rGO nanocomposites were an applicable additive for enhancing the charge collection properties in dye-sensitized solar cells (DSSCs), owing to its ability to reduce the charge-recombination pathways effectively and decrease the leakage current (Cho et al., 2016). More recently, Wang et al. reported that TiO₂/rGO composite based blocking layer is negatively effecting the energy barrier and series resistance between TiO₂ (Wang et al., 2014).

Therefore, it is believed that the induced of rGO in TiO₂ and its fabrication as TiO₂/rGO photoanodes in PSC utilizing the properties of graphene that have excellent electrical and optical properties merging with chemical stability in TiO₂ to increase PSC efficiency and to achieve good conductivity. Accordingly, the post annealing temperature dependence while synthesizing TiO₂-rGO solution and its performance as mesoporous layer in PSC is systematically studied in its surface morphologies, optical characteristic, chemical bonding analysis and current-voltage measurements.

1.3 Research Hypothesis

TiO₂ doped rGO that synthesized at different annealing temperature improve the performance of structural, optical, chemical bonding and electrical properties of TiO₂/rGO as fabricated in perovskite solar cell.

1.4 Research Gap

For research gap, there are two main findings of studies are discussed. First, it is studied from literature review that TiO_2 have three crystalline phase which are anatase, rutile and brookite. The phase changing often links to the annealing temperature used during synthesis. Previous work stated that TiO_2 will change its phase from anatase to rutile at annealing temperature of 700 °C and above (Fazli et al., 2016). Meanwhile the current study investigated annealing temperature from 450 °C to 650 °C with 100 °C increment that shown the presence of rutile phase in TiO_2 at 550 °C to 650 °C annealing temperature. This finding might surpassed the theory that only annealing temperature effecting the TiO_2 phase, might as well the surrounding atmosphere, the preparation methods or the type of chemicals used in preparing TiO_2 solution.

Secondly, in past few years, numerous perovskite fabrication has used mesoporous TiO_2 as electron transport material (ETM) with spiro-OMeTAD as HTM and $\text{CH}_3\text{NH}_3\text{PbI}_3$ as the absorber (Tonui et al., 2018). In the effort of finding the most reliable photovoltaic solar cells, research by research must be done to fully optimize the performances of solar cell. Then, the idea of doping the TiO_2 with rGO in conjunction with excellent properties of graphene has been introduced in DSSC as its photoanodes and has increased the efficiency of DSSC. In this wise, this research introduced the TiO_2 doped rGO in PSC configurations as its mesoporous layer with improvement in electrical properties of PSC.

1.5 Research Objectives

The aim of this research is to study the characterization of TiO₂ doped rGO (TiO₂/rGO) solution and its performance as thin mesoporous layer perovskite solar cell. In order to achieve the aim above, objectives of the research are as below:

- (i) To examine the effects of 450 °C, 550 °C and 650 °C annealing temperature on TiO₂ doped rGO by structural, optical, chemical bonding analysis and electrical.
- (ii) To fabricate CH₃NH₃PbI₃-based perovskite devices using spiro-OMeTAD as a hole transport layer and TiO₂ doped rGO as electron transport layer.

1.6 Scope of Research

This study focuses on modifying the electron transport layer in PSC. In this research, PSC is constructed with introduction of titanium dioxide doped reduced graphene oxide (TiO₂/rGO) layers as electron transport layer. The annealing temperature of titanium dioxide were varied at 450 °C, 550 °C and 650 °C. TiO₂ is prepared by using Titanium (IV) oxide nanopowder as precursor with addition of polyethylene glycol in its process. Meanwhile, for rGO solution, first the graphene oxide (GO) is prepared by using Improved Hummer's method, then the GO solution's obtained is chemically reduced to become rGO. Subsequently, the TiO₂ is doped with the rGO solution via nano-composite process to obtain the TiO₂/rGO mixture. Next, TiO₂/rGO is deposited by using spin coating technique for thin film characterization and fabricated as ETL to become perovskite solar cell.

Next, the performance analysis of TiO₂-rGO thin film and perovskite solar cell has been carried out focusing on its surface morphology, optical, chemical bonding structure and electrical properties. Various method are used to analyse this characteristic which are